

C023 - Easy Clear




Descripción:

C023 es un barniz transparente de alto contenido de sólidos fácil de aplicar, buena fluidez y brillo duradero. Se sugiere principalmente para pintores de manos rápidas.

Sustratos Recomendables:

- Hyflow basecoat

Aplicación del product:



100% Clear	50% Hardener	5-10% Thinner
C023	H070 SLOW	S21 SLOW
	H060 NORMAL	S11 NORMAL
	H070 SLOW	S19 FAST



15-16s / DIN 4 mm / 20°C



HVLP 1,3 - 1,4 mm(2 capas)
0,7 bar de presión de atomización
1 capa media + completa
50 µm



Evaporar 2-3 minutos entre capas
Evaporar 10 minutos antes de hornear
Hornear 20 minutos a 60°C. Temperatura panel



Onda Corta 10-15 minutos
Panel > 80cm de distancia al IR

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



Utilizar protección

Características del producto:

Specific Gravity: 0.985 kg/cm³

Flash Point: 25°C (77°F)

Solid Content: 46.2 % by weight

Coverage: 8 - 9 m²/l at 50-micron dry film thickness (theoretical)

SDS: Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.