

C071 - VOC Superior Clear




Product Description

A VOC compliant UHS Clearcoat. C071 offers a good sagging resistance and an extreme gloss with its 1.5 coat application. It dries within 25 minutes when low baked, and is easy to polish, if needed.

Suitable Substrates

- Hyflow basecoat
- Hydrobase basecoat

Product Application



C071 - Application Standard - HS

100%	50%	0-5%
C071	H050 – FAST	S719
	H060 – NORMAL	S711 or S811
	H070 – SLOW	S721 or S821
	H075 – EXTRA SLOW	S2040
	H076 - SPECIAL	S2050

C071 - Application Standard - UHS

100%	50%
C071	H082 – FAST
	H090 – NORMAL
	H092 – SLOW
	H096 – EXTRA SLOW
	H099 - SPECIAL

Apply based on weather conditions



16-18 sec / DIN 4 mm / 20 °C (68 °F)
Potlife: 60 minutes at 20°C

Potlife: 80 minutes at 20°C
Potlife 45 minutes at 20°C (68°F)



HVLP 1.3 – 1.4 mm
2.0 - 2.5 bar inlet pressure

HVLP 1.3 – 1.4 mm
2.0 - 2.5 bar inlet pressure




2 Regular Coats
50 – 60 micron per coat

1 light coat + 1 full coat
50- 60 microns per coat

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

C071 - VOC Superior Clear



5-7 minutes at 20 °C (68 °F) between coats and before low baking.

5-7 minutes at 20 °C (68 °F) before baking



30 mins at 60 °C panel temperature



Medium Long Wave 10-12 min
The object should be maintained at greater than 80 cm from source.



Wear suitable protection

Product Characteristics

VOC(2004/42/EC): N/A

2004/42/IIB (d) (420)420. The EU limit value for this product (product category IIB.d) in ready to use form is max 420g/ltr. The VOC content of this product in ready for use form is max. 420 g/l.

Specific Gravity: 0.993 kg/cm³

Flash Point: 27°C (80 °F)

Solid Content: 55.6 %

Coverage: 9 - 10 m²/l at 50-micron film thickness (theoretical)

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

C071 - VOC Superior Clear



SDS:

Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.