



C075 - Express L.E. Clear


Product Description

A VOC compliant UHS 2k clearcoat with good anti-sag and with excellent flow and gloss. It is a time and material saving clearcoat due to its 0.5 + 1 coat application process. Due to the reduction in the number of spray passes, considerable material and time saving can be achieved.

Suitable Substrates

- Hyflow Basecoat.
- Hydrobase Basecoat.

Product Application



100%	50%
C075	H082 FAST UHS HARDENER
	H090 NORMAL UHS HARDENER
	H092 SLOW UHS HARDENER
	H096 EXTRA SLOW UHS HARDENER
	H099 SPECIAL UHS HARDENER



18 - 20 sec / DIN 4 mm / 20 °C (68 °F)
Potlife: 60 minutes at 20°C




HVLP 1.3 – 1.4 mm
2.0 – 2.5 bar inlet pressure



1 Clinging coat + 1 full coat
50 – 60 micron

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

C075 - Express L.E. Clear

	<p>5-10 minutes at 20 °C (68 °F)</p>
	<p>25 Minutes at 60°C (140 °F) Panel Temperature.</p>
	<p>10-15 minutes medium wave The object should be maintained at greater than 80cm from source</p>
	<p>Wear suitable protection</p>

Product Characteristics

VOC(2004/42/EC):	<p>VOC (2004/42/EC): 2004/42/EC IIB (d) (420)420. The EU limit value for this product (product category IIB. d) in ready to use form is max 420g/ltr. The VOC content of this product in ready for use form is max. 420 g/l.</p>
Flash Point:	<p>24°C (74 °F)</p>
Solid Content:	<p>58 % by weight – ready to spray</p>
Coverage:	<p>9-10 m²/l at 50-micron film thickness (theoretical)</p>
SDS:	<p>Refer to the Safety Data Sheet</p>

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.