

P60 - 2K Primer Beige



Description:

A VOC compliant, high build, two component sanding primer surfacer with good vertical stability, good application and filling properties. It is especially easy to sand particularly for hand sanding applications. Direct to plastic with addition of plastic additive A230.


Suitable Substrates:

- Existing Finishes except TPA
- OEM Primer or EDP, sanded
- Hymax Polyester Putties
- Bare metal substrates must be pre-primed with wash primer 9700.
- Other available colors (Grey P62, Black P63, White P64, Red P65)


Product Application:



STIR P60 well before mixing



100% Clear	25% Hardener	5-25% Thinner
P60	H61 Hardener	S11



22-24 sec / DIN 4 mm / 20°C (68°F)
Potlife 4 hours / 20°C (68°F)




Compliant 1.6 – 1.8 mm
2.0 – 2.5 bar inlet pressure
HVLP 1.7-2.0 mm ; maximum 0.7 bar at the air-cap



2-3 coats
60 microns per coat

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

P60 - 2K Primer Beige



5-6 minutes at 20°C (68°F) between coats



Air dry overnight
30 mn. at 60°C (140°F)



10 – 15 mn. Short Wave
The object should be maintained at greater than 80cm from source



Initial Sanding with P500 - P600 grit
Final Sanding with P800 - P1000 grit



Initial Sanding with P320 grit
Final Sanding with P400 - P500 grit



Clean Surface to remove contamination prior to application of top coat



Hyflow Top Coat
Hydrobase Basecoats



Wear suitable protection

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

P60 - 2K Primer Beige




N.B:

Poor opacity solid colors: When the HyMix Pro system informs you that the solid color has poor opacity, we recommend the following: Add the relevant T-Series into the primer which will assist you in achieving a background that will enhance the color and save on unnecessary coats of the selected color thus allowing you to keep costs to a minimum.

Process:

Using the appropriate primer from our range mix:




100% Clear	25% Hardener	5-25% Thinner
P60	H61 Hardener	S11

All other processes remain the same as per the P60 TDS sheet on application, drying and sanding.


9960 Primer on Plastics Direct:

With the addition of A230, P60 can be applied direct to plastics without the need for a 1k plastic adhesion promotor (plastic primer)



100% Clear	25% Hardener	5-25% Thinner	15% Plastic Additive
P60	H61 Hardener	S11	A230

All other processes remain the same as per the P60 TDS sheet on application, drying and sanding.



Potlife 45-60 mins / 20°C (68°F)

Product Characteristics:

VOC(2004/42/EC):

485 g/l (EU limit value for this category IIB.c being max. 540g/l)

Specific Gravity:

1.666 kg/cm³

Flash Point:

25°C (77°F)

Solid Content:

67.8 % by weight – ready to spray

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

P60 - 2K Primer Beige



Coverage:

5.7-5.8 m² /l at 80 micron film thickness (theoretical)

SDS:

Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



technical-support@gpccoatings.com
color-support@gpccoatings.com

www.hymaxrefinish.com

REV-2 – 4/25