

Product Description

High quality 2K Clear for panel repair and overall re-spray. Excellent gloss and flow in combination with very good polish ability. It is extremely stable when applied on vertical surfaces and it can be overcoated within 24 hours without intermediate sanding.

Suitable Substrates

- Hyflow basecoat
- Hydrobase basecoat

Product Application

	4000/01	50 0/11	
$\prod_{i=1}^{n}$	100% Clear	50% Hardener H050 FAST	5-10% Thinner
		H060 NORMAL	
		H070 SLOW	S11 THINNER NORMAL
		H075 EXTRA SLOW	S21 THINNER FAST
		H076 SPECIAL HARDENER	
□ ↓	16-18 sec / DIN 4 mm / 20 °C (68 °F) Pot life 5h at 20°C		
>- -	HVLP 1.3 – 1.5 mm (2 spray passes) 2.0 - 2.5 bar inlet pressure		
	2 coats – 50 -60 microns per coat		
<mark>/†/†/</mark>	Flash off before increasing	temperature	

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



C010R – Scratch Resistant Clear





20 minutes at 60 °C panel temperature



Short Wave 8 min The object should be maintained at greater than 80cm from source.



Wear suitable protection

Product Characteristics

VOC(2004/42/EC):	2004/42/IIB (e) (840)530. The EU limit value for this product (product category IIB.e) in ready to use form is max 840g/ltr. The VOC content of this product in ready for use form is max. 530 g/l.		
Specific Gravity:	0.985 kg/cm ³		
Flash Point:	25°C (77 °F)		
Solid Content:	52.1 % by weight		
Coverage:	8 - 9 m²/l at 50-micron dry film thickness (theoretical)		
SDS:	Refer to the Safety Data Sheet		

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



i