C061R - 2K Superior Clear



Product Description

This 2-coats high solid Scratch Resistant Clearcoat. C061R is very easy to apply and exhibits an excellent sag resistance while delivering a superior high gloss finish

Suitable Substrates

- Hyflow
- Hydrobase

Product Application



100%	50%	0-5%
C061R	H050 – FAST	S19
	H060 – NORMAL	S11 or S13
	H070 – SLOW	S21 or S24
	H075 – EXTRA SLOW	S40
	H076 - SPECIAL	S50



 $16-18 \text{ sec} / \text{DIN 4 mm} / 20 \,^{\circ}\text{C} (68 \,^{\circ}\text{F})$ Potlife: 80 minutes at $20\,^{\circ}\text{C}$



HVLP 1.3 – 1.5 mm (2 spray passes)
2.0 - 2.5 bar inlet pressure



1 Medium – 1 full-Coat 50 – 60 micron



5-7 minutes at 20 °C (68 °F) between coats

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



C061R - 2K Superior Clear





Low Bake at 30 mins at 60 °C panel temperature



Medium Long Wave 8 min
The object should be maintained at greater than 80 cm from source.



Wear suitable protection

Prod	luct	Char	actei	istics
FIUU	IULL	Cilai	actei	IZLICZ

	2004/42/EC IIB (e) (840)437. The EU limit value for this product (product
VOC(2004/42/EC):	category IIB. e) in ready to use form is max 840g/ltr. The VOC content of this
	product in ready for use form is max. 437 g/l.

Specific Gravity: 1.009 kg/cm³

Flash Point: 27°C

Solid Content: 55.3 % by weight

Coverage: 8 - 9 m²/l at 25-micron film thickness (theoretical)

SDS: Refer to the Safety Data Sheet

 $Disclaimer: Users\ assume\ full\ responsibility\ for\ any\ consequences\ resulting\ from\ the\ incorrect\ usage\ of\ our\ products.$

