

Description:

A VOC compliant, high build, two component sanding primer surfacer with good vertical stability, good application and filling properties. It is especially easy to sand particularly for hand sanding applications. Direct to plastic with addition of plastic additive A230.

Suitable Substrates:

- Existing Finishes except TPA
- OEM Primer or EDP, sanded
- Hymax Polyester Putties
- Bare metal substrates must be pre-primed with wash primer 9700.
- Other available colors (Grey P62, Black P63, White P64, Red P65)

Product Application:



STIR P63 well before mixing



100% Clear	25% Hardener	5-25% Thinner
P63	H61 Hardener	S11



22-24 sec / DIN 4 mm / 20°C (68°F) Potlife 4 hours / 20°C (68°F)



Compliant 1.6 – 1.8 mm 2.0 – 2.5 bar inlet pressure HVLP 1.7-2.0 mm; maximum 0.7 bar at the air-cap



2-3 coats 60 microns per coat



? _† ? _† ?	5-6 minutes at 20°C (68°F) between coats
	Air dry overnight 30 mn. at 60°C (140°F)
	10 – 15 mn. Short Wave The object should be maintained at greater than 80cm from source
	Initial Sanding with P500 - P600 grit Final Sanding with P800 - P1000 grit
	Initial Sanding with P320 grit Final Sanding with P400 - P500 grit
	Clean Surface to remove contamination prior to application of top coat
	Hyflow Top Coat Hydrobase Basecoats
	Wear suitable protection






		23/0 Haruerier	3-43/0 HIIIIIIEI
	100% Clear	25% Hardener	5-25% Thinner
Process:	Using the appropriate primer from our range mix:		
<u>N.B:</u>	Poor opacity solid colors: When the HyMix Pro system informs you that the solid color has poor opacity, we recommend the following: Add the relevant T-Series into the primer which will assist you in achieving a background that will enhance the color and save on unnecessary coats of the selected color thus allowing you to keep costs to a minimum.		

9963 Primer on Plastics Direct:

With the addition of A230, P63 can be applied direct to plastics without the need for a 1k plastic adhesion promotor (plastic primer)



All other processes remain the same as per the P60 TDS sheet on application, drying and sanding.



Potlife 45-60 mins / 20°C (68°F)

Product Characteristics:

VOC(2004/42/EC):	485 g/l (EU limit value for this category IIB.c being max. 540g/l)
Specific Gravity:	1.666 kg/cm3
Flash Point:	25°C (77°F)
Solid Content:	67.8 % by weight – ready to spray





Coverage:	5.7-5.8 m2 /l at 80 micron film thickness (theoretical)
SDS:	Refer to the Safety Data Sheet

