

### **Description:**

A VOC compliant, high build, two component sanding primer surfacer with good vertical stability, good application and filling properties. It is especially easy to sand particularly for hand sanding applications. Direct to plastic with addition of plastic additive A230.

#### **Suitable Substrates:**

- Existing Finishes except TPA
- OEM Primer or EDP, sanded
- Hymax Polyester Putties
- Bare metal substrates must be pre-primed with wash primer P97.
- Other available colors (Grey P62, Black P63, White P64, Red P65)

### **Product Application:**



STIR P64 well before mixing

100% Clear	25% Hardener	5-25% Thinner
P64	H61 Hardener	S11
 22-24 sec / DIN 4 mm / 20° Potlife 4 hours / 20°C (68°F		
Compliant 1.6 – 1.8 mm 2.0 – 2.5 bar inlet pressure HVLP 1.7-2.0 mm ; maximu		
2-3 coats 60 microns per coat		



\t\t\\	5-6 minutes at 20°C (68°F) between coats
	Air dry overnight 30 mn. at 60°C (140°F)
	10 – 15 mn. Short Wave The object should be maintained at greater than 80cm from source
	Initial Sanding with P500 - P600 grit Final Sanding with P800 - P1000 grit
	Initial Sanding with P320 grit Final Sanding with P400 - P500 grit
	Clean Surface to remove contamination prior to application of top coat
	Hyflow Top Coat Hydrobase Basecoat
	Wear suitable protection

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.





	All other processes rer	main the same as per the P60 1	DS sheet on application
	P64	H61 Hardener	S11
	100% Clear	25% Hardener	5-25% Thinner
<u>Process:</u>	Using the appropriate primer from our range mix:		
<u>N.B:</u>	solid color has poor op T-Series into the prime will enhance the color	ors: When the HyMix Pro syste pacity, we recommend the follower which will assist you in achie and save on unnecessary coat eep costs to a minimum.	owing: Add the relevant ving a background that

### **P64 Primer on Plastics Direct:**

With the addition of A230, P64 can be applied direct to plastics without the need for a 1k plastic adhesion promotor (plastic primer)



į	100% Clear	25% Hardener	5-25% Thinner	15% Plastic Additive
Ł	P64	H61 Hardener	S11	A230

All other processes remain the same as per the P60 TDS sheet on application, drying and sanding.



Potlife 45-60 mins / 20°C (68°F)

#### **Product Characteristics:**

VOC(2004/42/EC):	485 g/l (EU limit value for this category IIB.c being max. 540g/l)
Specific Gravity:	1.666 kg/cm3
Flash Point:	25°C (77°F)
Solid Content:	67.8 % by weight – ready to spray

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.





Coverage:	5.7-5.8 m2 /l at 80 micron film thickness (theoretical)
SDS:	Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

