

# P900 – Universal Primer Grey



## Product Description

P900 Universal Primer is a 1k, fast dry, high build and easy to sand surfacer.

## Suitable Substrates:

- Old and Sound thermoset topcoats.
- Hymax polyester fillers.

## Product Application:




Genclean S241



100 parts Primebuild  
50-150 parts Thinner S11 or G6




HVLP: Nozzle: 1.6 to 2.2 mm



2 -3 Coats


S11 Thinner	Viscosity	Thickness
50%	45"	23 µ film thickness/each coat
100%	18"	15 µ film thickness/ each coat
150%	14"	12 µ film thickness/ each coat



Wait 5 to 10 minutes between coats.

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.


## P900 – Universal Primer Grey



Sandable after 20 to 40 minutes at 20°C for a thickness of 40 to 60 microns



Dry sand with P 320 grit paper



Can be overcoated with all Hymax topcoats except Hydrobase



Wear suitable protection

### **Product Characteristics:**

**VOC (2004/42/EC):** 700g/l

**Specific Gravity:** 1.25 kg/cm<sup>3</sup>

**Flash Point:** 20°C (70°F)

**Solid Content:** 52.3% by weight pre-dilution

**Coverage:** 6 m<sup>2</sup>/l at 20 micron film thickness (theoretical)

**SDS:** Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

## P900 – Universal Primer Grey



Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



[technical-support@gpccoatings.com](mailto:technical-support@gpccoatings.com)  
[color-support@gpccoatings.com](mailto:color-support@gpccoatings.com)

[www.hymaxrefinish.com](http://www.hymaxrefinish.com)

REV-2 – 4/25