

### Product Description

Premium quality High Solid Scratch Resistant Clearcoat especially designed for bodyshops looking for competitive quality and customers' satisfaction. C021 Clear is an anti-sag clearcoat and has an ultimate gloss, direct from the gun.

#### Suitable Substrates:

• Hyflow basecoat

i

- Sound OEM finishing
- Thermoset finishing

#### **Product Application**

	100% Clear	50% Hardener	5-10% Thinner	
		H050 - FAST	S19 - FAST	
.⊓	C021	H060 - NORMAL	S11 – NORMAL	
		H070 - SLOW	S21 – SLOW	
<b>□</b> <b>↓</b> <sup>s</sup>	16-18s / DIN 4 mm / 20 °C Potlife: 5h at 20°C			
	HVLP 1.3 – 1.5 mm (2 coats) 1 medium + full coat 50-60 μm			
<mark>?t?t?</mark>	Flash off 2-3 minutes between coats 10 minutes before low bake			
LOW BAKE	Low Bake 20 min at 60 °C panel temperature			

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



# **C021 - Versatile Clear**





Short Wave 10-15 min Panel > 80cm from IR unit.



Wear suitable protection

## **Product Characteristics**

VOC(2004/42/EC):	TO BE DETERMINED	
Specific Gravity:	0.985 kg/cm <sup>3</sup>	
Flash Point:	25 <sup>o</sup> C (77 °F)	
Solid Content:	52.1 % by weight	
Coverage:	8 - 9 m²/l at 50 micron dry film thickness (theoretical)	
SDS:	Refer to the Safety Data Sheet	

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

