

Product Description

This 2-coats high solid Scratch Resistant Clearcoat. C061R is very easy to apply and exhibits an excellent sag resistance while delivering a superior high gloss finish

Suitable Substrates

- Hyflow
- Hydrobase

Product Application



	100%	50%	0-5%
	C061R	H050 – FAST	S19
		H060 – NORMAL	S11 or S13
		H070 – SLOW	S21 or S24
		H075 – EXTRA SLOW	S40
		H076 - SPECIAL	S50

_.....

_.....

.....



16-18 sec / DIN 4 mm / 20 °C (68 °F) Potlife: 80 minutes at 20°C



HVLP 1.3 – 1.5 mm (2 spray passes) 2.0 - 2.5 bar inlet pressure



1 Medium – 1 full-Coat 50 - 60 micron



5-7 minutes at 20 °C (68 °F) between coats

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



C061R - 2K Superior Clear





Low Bake at 30 mins at 60 °C panel temperature



Medium Long Wave 8 min The object should be maintained at greater than 80 cm from source.



Wear suitable protection

Product Characteristics

VOC(2004/42/EC):	 2004/42/EC IIB (e) (840)437. The EU limit value for this product (product 2/EC): category IIB. e) in ready to use form is max 840g/ltr. The VOC content of this product in ready for use form is max. 437 g/l. 	
Specific Gravity:	1.009 kg/cm ³	
Flash Point:	27°C	
Solid Content:	55.3 % by weight	
Coverage:	8 - 9 m²/l at 25-micron film thickness (theoretical)	
SDS:	Refer to the Safety Data Sheet	

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



I.