

### **Description:**

A VOC compliant, high build, two component sanding primer surfacer with good vertical stability, good application and filling properties. It is especially easy to sand particularly for hand sanding applications. Direct to plastic with addition of plastic additive A230.

#### **Suitable Substrates:**

- Existing Finishes except TPA
- OEM Primer or EDP, sanded
- Hymax Polyester Putties
- Bare metal substrates must be pre-primed with wash primerP97.
- Other available colors (Grey P62, Black P63, White P64, Red P65)

### **Product Application:**



STIR P62 well before mixing



100% Clear	25% Hardener	5-25% Thinner
P62	H61 HARDENER	S11



22-24 sec / DIN 4 mm / 20°C (68°F) Potlife 4 hours / 20°C (68°F)



Compliant 1.6 - 1.8 mm 2.0 – 2.5 bar inlet pressure HVLP 1.7-2.0 mm; maximum 0.7 bar at the air-cap



2-3 coats 60 microns per coat





\t\t\	5-6 minutes at 20°C (68°F) between coats
	Air dry overnight 30 mn. at 60°C (140°F)
	10 – 15 mn. Short Wave The object should be maintained at greater than 80cm from source
· e	Initial Sanding with P500 - P600 grit Final Sanding with P800 - P1000 grit
	Initial Sanding with P320 grit Final Sanding with P400 - P500 grit
	Clean Surface to remove contamination prior to application of top coat
	Hyflow Top Coat Hydrobase Basecoats
	Wear suitable protection





<u>N.B:</u>	color has poor opacity, into the primer which was a second control of the which which which which which which was a second control of the which which which which which was a second control of the which which which which which which which was a second control of the which whic	rs: When the HyMix Pro syster we recommend the following: will assist you in achieving a baunnecessary coats of the selectosts to a minimum.	Add the relevant T-Series ckground that will enhance
Process:	Using the appropriate p	orimer from our range mix:	
	100% Clear	25% Hardener	5-25% Thinner
	P62	H61 Hardener	S11
	All other processes renderlying and sanding.	nain the same as per the P60 T	DS sheet on application,

### 9962 Primer on Plastics Direct:

With the addition of A230, P62 can be applied direct to plastics without the need for a 1k plastic adhesion promotor (plastic primer)



100% Clear	25% Hardener	5-25% Thinner	15% Plastic Additive
P62	H61 Hardener	S11	A230

All other processes remain the same as per the P60 TDS sheet on application, drying and sanding.



Potlife 45-60 mins / 20°C (68°F)

### **Product Characteristics:**

VOC(2004/42/EC):	485 g/l (EU limit value for this category IIB.c being max. 540g/l)
Specific Gravity:	1.666 kg/cm3
Flash Point:	25°C (77°F)
Solid Content:	67.8 % by weight – ready to spray





Coverage:	5.7-5.8 m2 /l at 80 micron film thickness (theoretical)
SDS:	Refer to the Safety Data Sheet

